

Infino LT-1100

Polycarbonate

LOTTE ADVANCED MATERIALS CO., LTD.

PROSPECTOR[®]

www.ulprospector.com

Technical Data

Product Description

Infino LT-1100 is a Polycarbonate (PC) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

General

Material Status	• Commercial: Active		
Literature ¹	• Processing (English) • Technical Information - ASTM (English) • Technical Information - ISO (English)		
UL Yellow Card ²	• E115797-101752045		
Search for UL Yellow Card	• LOTTE ADVANCED MATERIALS CO., LTD. • Infino		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America

Physical	Nominal Value Unit	Test Method
Density / Specific Gravity (Natural)	1.19 g/cm ³	ASTM D792 ISO 1183
Melt Mass-Flow Rate (MFR)		ASTM D1238 ISO 1133
250°C/10.0 kg	25 g/10 min	
300°C/1.2 kg	11 g/10 min	
Molding Shrinkage		
Flow : 3.20 mm	0.50 to 0.80 %	ASTM D955
Across Flow : 3.20 mm	0.60 to 0.90 %	ASTM D955
Across Flow : 2.00 mm	0.60 to 0.90 %	ISO 294-4
Flow : 2.00 mm	0.50 to 0.80 %	ISO 294-4

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus		
-- ⁴	2200 MPa	ASTM D638
--	2100 MPa	ISO 527-2/50
Tensile Strength		
Yield ⁴	63.0 MPa	ASTM D638
Yield	62.0 MPa	ISO 527-2/50
Break ⁴	65.0 MPa	ASTM D638
Break	64.0 MPa	ISO 527-2/50
Tensile Elongation		
Break ⁴	110 %	ASTM D638
Break	91 %	ISO 527-2/50
Flexural Modulus		
-- ⁵	2300 MPa	ASTM D790
-- ⁶	2200 MPa	ISO 178
Flexural Strength		
-- ⁵	90.0 MPa	ASTM D790
-- ⁶	91.0 MPa	ISO 178

Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength ⁷ (23°C)	78 kJ/m ²	ISO 179/1eA
Notched Izod Impact		
23°C, 3.18 mm	850 J/m	ASTM D256
23°C, 6.35 mm	150 J/m	ASTM D256
23°C ⁷	69 kJ/m ²	ISO 180/1A

Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (R-Scale)	122	ASTM D785 ISO 2039-2



Infino LT-1100

Polycarbonate

LOTTE ADVANCED MATERIALS CO., LTD.

PROSPECTOR®

www.ulprospector.com

Thermal	Nominal Value Unit	Test Method
Heat Deflection Temperature		
0.45 MPa, Unannealed, 4.00 mm	137 °C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	135 °C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	124 °C	ISO 75-2/A
Vicat Softening Temperature	144 °C	ISO 306/B50

Injection	Nominal Value Unit
Drying Temperature	
Desiccant Dryer	110 °C
Hot Air Dryer	120 °C
Drying Time	
Desiccant Dryer	4.0 hr
Hot Air Dryer	4.0 hr
Suggested Max Moisture	0.050 %
Rear Temperature	260 to 270 °C
Middle Temperature	270 to 280 °C
Front Temperature	285 to 295 °C
Nozzle Temperature	290 °C
Mold Temperature	50 to 60 °C
Injection Pressure	7.85 MPa
Back Pressure	3.92 to 5.88 MPa
Screw Speed	60 to 80 rpm

Injection Notes

Hot Runner Temperature: 270 to 290°C

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

³ Typical properties: these are not to be construed as specifications.

⁴ 50 mm/min

⁵ 2.8 mm/min

⁶ 2.0 mm/min

⁷ 4mm

